

Construction Standard Testing Concrete

Volume 1

Amendment sheet no. 1101 : September 1992

The following amendments are made to CS 1:1990, Volume 1 :

1. General Notes, para. 1(c), p.8 : replace by

(c) If any test is performed on a specimen which does not fully comply with this Standard (e.g. a cube which has not been cured in accordance with Section 10) or if the test itself does not fully conform to the requirements of this Standard, the relevant details must be recorded in the Report.

2. Appendix A, Clause A2, p.35 : replace by

A2 Sample tray

The sample tray shall be at least 900mm x 900mm in area, made of metal and have sufficient capacity to contain the concrete sample. It shall have sides to prevent the loss of water or cement paste.